

**Honeywell PTM5000 Series
Phase Change Thermal
Interface Material**

Honeywell PTM5000 Series Phase Change Thermal Interface Material

**HIGHLY THERMALLY CONDUCTIVE
PHASE CHANGE MATERIAL
IN PAD AND DISPENSE FORMATS**

BENEFITS


- High performance filler and polymer technology
- Phase change at 45°C
- Highly conductive filler with tailored loading to optimize performance
- Superior handling and reworkability
- Reliable thermal performance

FEATURES

- Key outputs in thermal impedance for The PTM5000 Series have been measured to fit individual needs.

OVERVIEW

Honeywell's PTM5000 Series, a highly thermally conductive Phase Change Material (PCM) in both pad and dispense formats, is designed to minimize thermal resistance at interfaces, maintain excellent performance through reliability testing, and provide scalable application at a competitive cost.



Based on a novel polymer PCM system, this material exhibits excellent wetting at interfaces during typical operating temperature ranges, resulting in very low surface contact resistance.


A proprietary filler material provides high thermal conductivity (4.4 W/m-K) and low thermal impedance ($<0.16^{\circ}\text{C-cm}^2/\text{W}$ @ 2 mil), making the PTM5000 Series desirable for high performance integrated circuit devices.

APPLICATIONS

Clamping pressure and temperature are suggested to achieve a minimum bond line thickness of the thermal interface material, typically less than 1.5 mil (0.038mm) for best performance. The material must go through the phase change temperature in order to exhibit entitlement performance.

Roll Format Tape:

- Plastic liner
- 10 mil (0.25mm) thickness supplied



Physical Properties

Thermal Conductivity	4.4 W/m-K
Thermal Impedance @ 50µm	0.14°C-cm²/W
@ ~20µm	0.06°C-cm²/W
Volume Resistivity	$3.0 \times 10^{15} \Omega\text{-cm}$
Specific Gravity	2.3 g/cm³
Typical Bond Line Thickness (No Shim @ 40 PSI)	0.6 mil

Storage & Use

Shelf Life	1 Year at 25°C
------------	----------------

Thermal Impedance Post Reliability

End of Line	0.10°C-cm²/W
Temperature Cycling "B" (-55°C to 125°C, 1000 cycles)	0.07°C-cm²/W
Bake 125°C, 1000 h	0.08°C-cm²/W
Bake 150°C, 1000 h	0.07°C-cm²/W
HAST, 96 h	0.09°C-cm²/W
85°C, 85% RH, 1000 h	0.11°C-cm²/W



RESPONSIBLE CARE®
OUR COMMITMENT TO SUSTAINABILITY

Honeywell Electronic Materials

USA: 1-509-252-2102

China: 86-21-28942481

Germany: 49-5137-999-9199

Japan: 81-3-6730-7092

Korea: 82-2-3483-5076

Singapore: 65-6580-3593

Taiwan: 886-3-6580300 ext.312

www.honeywell-pmt.com/sm/em/

Although all statements and information contained herein are believed to be accurate and reliable, they are presented without guarantee or warranty of any kind, express or implied. Information provided herein does not relieve the user from the responsibility of carrying out its own tests and experiments, and the user assumes all risks and liability for use of the information and results obtained. Statements or suggestions concerning the use of materials and processes are made without representation or warranty that any such use is free of patent infringement and are not recommendations to infringe any patent. The user should not assume that all toxicity data and safety measures are indicated herein or that other measures may not be required. PB1440315Rev8
©2015 Honeywell International Inc.

Honeywell